SBG2UC1

Grade: Standard

Strong base type 2 anion resin, styrene/DVB gel, chloride form

ResinTech SBG2-UC1 is a chloride form type 2 gel strong base anion resin. Type 2 anion resins have lower selectivities and therefore higher chemical efficiency and better resistance to fouling than type 1 anion resins. SBG2-UC1 is intended for industrial use in chloride form for dealkalization and removal of contaminants such as nitrate, arsenate, chromate, uranium, etc., and can also be regenerated into the hydroxide form and used in various demineralization configurations.

FEATURES & BENEFITS

- High operating capacity
- Multiple contaminant removal
- Superior physical stability
- Complies with US FDA regulations

APPLICATIONS

- Dealkalizer
- Demineralization / DI
- Trace Contaminant Removal

PHYSICAL PROPERTIES

Polymer Matrix	Styrene/DVB
Polymer Type	Gel
Ionic Form (as shipped)	Chloride (Cl^-)
Functional Group	Dimethylethanolamine
Physical Form	Spherical Beads
Uniformity Coefficient	1.10
< 50 mesh (300 µm) %	< 1%
Minimum Sphericity (%)	93
Reversible Swelling	8 to 12% (Cl → OH)
Capacity (meq/mL)	1.40
Moisture Retention (%)	36 to 45
Shipping Weight	43 - 45 lbs/cu.ft. (689 - 721 g/L)
Color	White To Amber

SUGGESTED OPERATING CONDITIONS

Maximum Temperature	170°F (77°C)
Maximum Pressure Loss	20 psi (138 kPa)
Backwash Expansion (%)	25 - 50
Flow Rate	
Working Service	1-10 gpm/cu.ft. (8-80 BV/h)

REGENERATION DETAILS

Salt Cycle (NaCl)	2% - 10%
Displacement Flow Rate	Same as dilution water
Displacement Volume	10-15 gals/cu.ft. (1-2 BV)
Rinse Volume	Minimum of 30 gals/cu.ft. (4 BV)

Conforms to §21CFR173.25 of the USFDA Food Additives Regulations

RESINTECH® INC.
INNOVATIONS IN ION EXCHANGE

CORPORATE HEADQUARTERS 1801 Federal Street Camden, NJ 08105 USA PHONE 856.768.9600 EMAIL info@resintech.com WEB resintech.com

SBG2UC1

BACKWASH EXPANSION



The graph above shows the expansion characteristics of ResinTech SBG2UC1 as a function of flow rate at various temperatures.

TRACE CONTAMINANT REMOVAL (U, Cr, As, Se, ClO4)

ResinTech **SBG2** has high capacity in the chloride form and can be used to remove a variety of trace contaminants, even when that contaminant is not highly preferred compared to the other bulk ions in the feed water. Useful capacities are obtained when the feed TDS is substantially less than the resinÕs internal TDS. Uranium, chromate, and perchlorate are particularly well removed. Arsenate and selenate are well removed but can be chromatographically displaced by sulfate and other ions.

NITRATE REMOVAL

ResinTech **SBG2** can be used in the chloride cycle to reduce nitrates along with sulfates. Although high operating capacities and high salt efficiency can be obtained, there is also the possibility of nitrate dumping. Use of chloride form anion resin reduces pH during the early portion of the exhaustion cycle. When treating waters with high hardness the brine dilution and displacement waters should be softened and a low hardness salt used to prevent scaling during regeneration.

DEMINERALIZATION

See ResinTech **SBG2-OH**.

CERTIFICATIONS

Meets NSF/ANSI/CAN 61

Meets NSF/ANSI/CAN 372

REACH Registered

PACKAGING

Standard

42 cu.ft. Supersack | 7 cu.ft. Drum
200L Drum | 1000L Supersack

Metric

1 cu.ft. Bag | 5 cu.ft. Drum
25L Bag | 140L Drum

Shipping Weight

43 - 45 lbs/cu.ft. (689 - 721 g/L)

RESINTECH® INC.
INNOVATIONS IN ION EXCHANGE

CORPORATE HEADQUARTERS 1801 Federal Street Camden, NJ 08105 USA PHONE 856.768.9600 EMAIL info@resintech.com WEB resintech.com

MATERIAL SAFETY DATA SHEETS (MSDS)

Material Safety Data Sheets (MSDS) are available for all products on the ResinTech website. They contain important health and safety information that may be needed to protect your employees and customers from any known health and safety hazards associated with our products. We recommend that you secure and study the pertinent MSDS for our products and any other products being used.

These suggestions and data are based on information we believe to be reliable. They are offered in good faith. However we do not make any guarantee or warranty. We caution against using these products in an unsafe manner or in violation of any patents; further we assume no liability for the consequences of any such actions.

Safety Data Sheets (SDS) are available at resintech.com

RESINTECH® INC.
INNOVATIONS IN ION EXCHANGE

CORPORATE HEADQUARTERS 1801 Federal Street Camden, NJ 08105 USA PHONE 856.768.9600 EMAIL info@resintech.com WEB resintech.com