WACMP

Grade: Standard

Weak acid cation resin, acrylic/DVB macroporous, hydrogen form

ResinTech WACMP is a hydrogen form macroporous weak acid cation resin. It has exceptionally high capacity and can be regenerated at close to 100% acid efficiency but is limited to use in alkaline waters with pH greater than 7. WACMP is intended for hardness removal from waters that contain significant alkalinity and for demineralization where the use of a weak acid cation resin is required.

FEATURES & BENEFITS

- Macroporous structure
- High regeneration efficiency
- Superior physical stability
- Controlled particle size
- Complies with US FDA regulations

APPLICATIONS

- Dealkalizer
- Lead Removal
- Temporary Hardness Removal
- Brackish
- Chloride Brines
- Condensate
- High pH Solutions
- Neutral Water
- Potable Water
- Produced Water

PHYSICAL PROPERTIES

Polymer Matrix	Acrylic/DVB
Polymer Type	Macroporous
Ionic Form (as shipped)	Hydrogen (H^+)
Functional Group	Carboxylic Acid
Physical Form	Spherical Beads
Uniformity Coefficient	1.60
Particle Size	16-50 US mesh (297-1190µm)
< 50 mesh (300 µm) %	< 1%
Minimum Sphericity (%)	93
Reversible Swelling	50 to 60% (H → Na)
Capacity (meq/mL)	3.80
Moisture Retention (%)	43 to 60
Shipping Weight	47 - 49 lbs/cu.ft. (753 - 785 g/L)
Color	White to Cream
Regenerable	Regenerable

SUGGESTED OPERATING CONDITIONS

Maximum Temperature	212°F (100°C)	Flow Rate	
Minimum Bed Depth	24 in. (61.0 cm)	Working Service	1-5 gpm/cu.ft. (8-40 BV/h)

Conforms to §21CFR173.25 of the USFDA Food Additives Regulations

RESINTECH® INC.
INNOVATIONS IN ION EXCHANGE

CORPORATE HEADQUARTERS 1801 Federal Street Camden, NJ 08105 USA PHONE 856.768.9600 EMAIL info@resintech.com WEB resintech.com

REGENERATION DETAILS

Hydrogen Cycle (HCl)	1 to 5%	Displacement Volume	10-15 gals/cu.ft. (1-2 BV)
Regenerant Flow Rate	0.3-1.5 gpm/cu.ft. (2-12 BV/h)	Rinse Flow Rate	Same as service flow
Regenerant Contact Time	> 30 minutes	Rinse Volume	10-15 gals/cu.ft. (1-2 BV)
Displacement Flow Rate	Same as dilution water		

PRESSURE LOSS



The graph above shows the expected pressure loss of ResinTech WACMP per foot of bed depth as a function of flow rate at various temperatures.

BACKWASH EXPANSION



The graph above shows the expansion characteristics of ResinTech WACMP as a function of flow rate at various temperatures.

CAPACITY



Capacity and leakage data are based on the following: 2:1 Ca:Mg ratio, 500 ppm TDS as CaCO3, 0.2% hardness in the salt and 10% brine concentration applied co-currently through the resin over 30 minutes. No engineering downgrade has been applied.

CAPACITY 2



Capacity and leakage data are based on the following: 2:1 Ca:Mg ratio, 500 ppm TDS as CaCO3, 0.2% hardness in the salt and 10% brine concentration applied co-currently through the resin over 30 minutes. No engineering downgrade has been applied.

SOFTENER AND DEALKALIZER

ResinTech **WACMP** removes hardness from water by neutralizing alkalinity from HCO_3 to CO_2. The carbon dioxide can then be removed in a degassifier. For complete removal of hardness, a strong acid cation type softener is needed. For complete conversion of HCO_3 alkalinity to CO_2, a hydrogen form cation may be needed.

HIGH TDS SOFTENING

ResinTech **WACMP** can be operated as a softener in the sodium cycle. Selectivity for hardness compared to sodium is between 5 and 10 times higher than conventional softening resins. Regeneration requires acid followed by caustic, salt can not be used. Sodium form weak acid resins can be used to soften high TDS waters up to approximately 50,000 ppm.

RESINTECH® INC.
INNOVATIONS IN ION EXCHANGE

CORPORATE HEADQUARTERS 1801 Federal Street Camden, NJ 08105 USA PHONE 856.768.9600 EMAIL info@resintech.com WEB resintech.com

METALS REMOVAL

ResinTech **WACMP** has higher selectivity for divalent transition metals as compared to hardness ions.

CERTIFICATIONS

Meets NSF/ANSI/CAN 61

Kosher Certified

REACH Registered

PACKAGING

Standard

1 cu.ft. Bag | 42 cu.ft. Supersack
25 L bag | 1000 L Supersack

Metric

5 cu.ft. Drum | 7 cu.ft. Drum
140L Drum | 200L Drum

Shipping Weight

47 - 49 lbs/cu.ft. (753 - 785 g/L)

MATERIAL SAFETY DATA SHEETS (MSDS)

Material Safety Data Sheets (MSDS) are available for all products on the ResinTech website. They contain important health and safety information that may be needed to protect your employees and customers from any known health and safety hazards associated with our products. We recommend that you secure and study the pertinent MSDS for our products and any other products being used.

These suggestions and data are based on information we believe to be reliable. They are offered in good faith. However we do not make any guarantee or warranty. We caution against using these products in an unsafe manner or in violation of any patents; further we assume no liability for the consequences of any such actions.

Safety Data Sheets (SDS) are available at resintech.com

RESIN TECH® INC.
INNOVATIONS IN ION EXCHANGE

CORPORATE HEADQUARTERS 1801 Federal Street Camden, NJ 08105 USA PHONE 856.768.9600 EMAIL info@resintech.com WEB resintech.com