MBD-10-NG

Grade: Nuclear

Mixed bed resin, styrene/DVB gel, nuclear grade, hydrogen & hydroxide form

ResinTech MBD-10 is a nuclear grade mixture of a dark colored hydrogen form cation resin and a hydroxide form type 1 strong base anion resin. The resin ratio is 1:1 on an equivalent basis and the component resins are chosen to separate easily for regeneration. MBD-10 is intended for use in all mixed bed deionization applications that require high resistivity and high throughput capacity.

FEATURES & BENEFITS

- Highest operating capacity
- Ease of separation
- Superior thermal and physical stability
- Ideal for portable exchange DI systems
- Complies with US FDA regulations

APPLICATIONS

- Cartridge Applications
- Demineralization / DI
- Portable Exchange Deionization (PEDI)

PHYSICAL PROPERTIES

Particle Size	16-50 US mesh (297-1190µm)
< 50 mesh (300 µm) %	< 1%
Reversible Swelling	12 to 17% (H+/OH- , Na+/Cl-)
Shipping Weight	42 - 44 lbs/cu.ft. (673 - 705 g/L)

SUGGESTED OPERATING CONDITIONS

Maximum Temperature	140°F (60°C)
Minimum Bed Depth	24 in. (61.0 cm)
Maximum Pressure Loss	25 psi (172 kPa)
Operating pH Range	2.0 to 12.0
Flow Rate	
Working Service	1-5 gpm/cu.ft. (8-40 BV/h)
Polishing	3-15 gpm/cu.ft. (24-120 BV/h)

CERTIFICATIONS

REACH Registered

Conforms to §21CFR173.25 of the USFDA Food Additives Regulations

PACKAGING

Standard

7 cu.ft. Drum | 42 cu.ft. Supersack

200L Drum | 1000L Supersack

Metric

1 cu.ft. Bag | 5 cu.ft. Drum

25L Bag | 140L Drum

Shipping Weight

42 - 44 lbs/cu.ft. (673 - 705 g/L)

RESINTECH® INC.
INNOVATIONS IN ION EXCHANGE

CORPORATE HEADQUARTERS 1801 Federal Street Camden, NJ 08105 USA PHONE 856.768.9600 EMAIL info@resintech.com WEB resintech.com

MATERIAL SAFETY DATA SHEETS (MSDS)

Material Safety Data Sheets (MSDS) are available for all products on the ResinTech website. They contain important health and safety information that may be needed to protect your employees and customers from any known health and safety hazards associated with our products. We recommend that you secure and study the pertinent MSDS for our products and any other products being used.

These suggestions and data are based on information we believe to be reliable. They are offered in good faith. However we do not make any guarantee or warranty. We caution against using these products in an unsafe manner or in violation of any patents; further we assume no liability for the consequences of any such actions.

Safety Data Sheets (SDS) are available at resintech.com

RESIN TECH® INC.
INNOVATIONS IN ION EXCHANGE

CORPORATE HEADQUARTERS 1801 Federal Street Camden, NJ 08105 USA PHONE 856.768.9600 EMAIL info@resintech.com WEB resintech.com