SBG1-OH-NANO

Strong base type 1 anion resin, styrene/DVB gel, nano grade, hydroxide form

ResinTech SBG1-OH-NANO is a type 1 gel strong base anion resin in the hydroxide form. The NANO grade has been functionally tested to produce >18 megohm resistivity and under 2 ppb of TOC (when mixed with ULTRA grade cation resin). SBG1-OH-NANO is intended for use in polishing demineralizing applications such as mixed beds where a resin that has been tested to confirm high resistivity and the lowest possible TOC is required.

FEATURES & BENEFITS

- Lowest TOC leach rate
- Ultrapure water production
- Controlled particle size
- Superior physical stability

APPLICATIONS

- Anion Component in Mixed Beds

REACH Registered

RESINTECH® INC.
INNOVATIONS IN ION EXCHANGE

CORPORATE HEADQUARTERS 1801 Federal Street Camden, NJ 08105 USA PHONE 856.768.9600 EMAIL info@resintech.com WEB resintech.com

SBG1-OH-NANO

Polymer Matrix	Styrene/DVB
Polymer Type	Gel
Ionic Form (as shipped)	Hydroxide (OH^-)
Functional Group	Trimethylamine
Physical Form	Spherical Beads
Particle Size US Mesh (µm)	16 (1190) to 50 (297)
< 50 mesh (300 µm) %	< 1
Minimum Sphericity (%)	93
Reversible Swelling	18 to 25% (Cl → OH)
Uniformity	Gaussian
Uniformity Coefficient	1.60
Capacity (meq/mL)	1.20
Moisture Retention (%)	52 to 60
Color	White To Amber

SUGGESTED OPERATING CONDITIONS

Maximum Temperature	140°F (60°C)
Maximum Pressure Loss	20 psi (138 kPa)
Backwash Expansion (%)	25 - 50
Flow Rate	
Working Service	Depends on fluid viscosity. Contact ResinTech

REGENERATION DETAILS

Hydroxide Cycle (NaOH)	2 to 6%
Displacement Flow Rate	Same as dilution water
Displacement Volume	10-15 gals/cu.ft. (1-2 BV)

PACKAGING

Standard

42 cu.ft. Supersack | 7 cu.ft. Drum
1 cu.ft. Bag | 5 cu.ft. Drum

Metric

25L Bag | 140L Drum

SAFETY DATA SHEETS (SDS)

Safety Data Sheets (SDS) are available for all products on the ResinTech website. They contain important health and safety information that may be needed to protect your employees and customers from any known health and safety hazards associated with our products. We recommend that you secure and study the pertinent MSDS for our products and any other products being used.

These suggestions and data are based on information we believe to be reliable. They are offered in good faith. However we do not make any guarantee or warranty. We caution against using these products in an unsafe manner or in violation of any patents; further we assume no liability for the consequences of any such actions.

Safety Data Sheets (SDS) are available at resintech.com

RESINTECH® INC.
INNOVATIONS IN ION EXCHANGE

CORPORATE HEADQUARTERS 1801 Federal Street Camden, NJ 08105 USA PHONE 856.768.9600 EMAIL info@resintech.com WEB resintech.com