SBG2-OH-NG

Strong base type 2 anion resin, styrene/DVB gel, hydroxide form

ResinTech SBG2-OH-NG is a nuclear grade type 2 gel strong base anion resin in the hydroxide form. SBG2-OH-NG has higher chemical efficiency and better resistance to fouling than type 1 anion resins. SBG2-OH-NG is intended for industrial demineralization applications where regeneration efficiency is important and operating temperatures are not excessive.

FEATURES & BENEFITS

- High operating capacity
- Multiple contaminant removal
- Superior physical stability
- Complies with US FDA regulations

APPLICATIONS

- Industrial Demineralization
- Demineralization of Organic-Laden Water

REACH Registered

RESINTECH® INC.
INNOVATIONS IN ION EXCHANGE

CORPORATE HEADQUARTERS 1801 Federal Street Camden, NJ 08105 USA PHONE 856.768.9600 EMAIL info@resintech.com WEB resintech.com

SBG2-OH-NG

Polymer Matrix	Styrene/DVB
Polymer Type	Gel
Ionic Form (as shipped)	Hydroxide (OH^-)
Functional Group	Dimethylethanolamine
Physical Form	Spherical Beads
Particle Size US Mesh (µm)	16 (1190) to 50 (297)
< 50 mesh (300 µm) %	< 1
Minimum Sphericity (%)	93
Reversible Swelling	8 to 12% (Cl → OH)
Uniformity	Gaussian
Uniformity Coefficient	1.60
Capacity (meq/mL)	1.00
Moisture Retention (%)	NA**
Shipping Weight	43 - 45 lbs/cu.ft. (689 - 721 g/L)
Color	Orange to Dark Red

SUGGESTED OPERATING CONDITIONS

Maximum Temperature	95°F (35°C)
Maximum Pressure Loss	20 psi (138 kPa)
Backwash Expansion (%)	25 - 50
Flow Rate	
Working Service	Depends on fluid viscosity. Contact ResinTech

REGENERATION DETAILS

Hydroxide Cycle (NaOH)	2 to 6%
Displacement Flow Rate	Same as dilution water
Displacement Volume	10-15 gals/cu.ft. (1-2 BV)

PACKAGING

Standard

42 cu.ft. Supersack | 7 cu.ft. Drum
1 cu.ft. Bag | 5 cu.ft. Drum

Metric

25L Bag | 140L Drum

SAFETY DATA SHEETS (SDS)

Safety Data Sheets (SDS) are available for all products on the ResinTech website. They contain important health and safety information that may be needed to protect your employees and customers from any known health and safety hazards associated with our products. We recommend that you secure and study the pertinent MSDS for our products and any other products being used.

These suggestions and data are based on information we believe to be reliable. They are offered in good faith.
However we do not make any guarantee or warranty. We caution against using these products in an unsafe manner or in violation of any patents; further we assume no liability for the consequences of any such actions.

Safety Data Sheets (SDS) are available at resintech.com

RESINTECH® INC.
INNOVATIONS IN ION EXCHANGE

CORPORATE HEADQUARTERS 1801 Federal Street Camden, NJ 08105 USA PHONE 856.768.9600 EMAIL info@resintech.com WEB resintech.com