CG10-MG

Grade: Standard

Strong acid cation resin, styrene/DVB 10% crosslinked gel, medical grade, sodium form

APPLICATIONS

- Softening

PHYSICAL PROPERTIES

Polymer Matrix	Styrene/DVB
Polymer Type	Gel
Ionic Form (as shipped)	Sodium (Na^+)
Functional Group	Sulfonic Acid
Physical Form	Spherical Beads
Uniformity Coefficient	1.60
Particle Size	16-50 US mesh (297-1190µm)
< 50 mesh (300 µm) %	< 1%
Minimum Sphericity (%)	95
Reversible Swelling	4 to 8% (Na → H)
Capacity (meq/mL)	2.20
Moisture Retention (%)	39 to 45
Shipping Weight	52 - 54 lbs/cu.ft. (833 - 865 g/L)
Color	Amber
Regenerable	Regenerable

SUGGESTED OPERATING CONDITIONS

Maximum Temperature	280°F (138°C)
Minimum Bed Depth	24 in. (61.0 cm)
Maximum Pressure Loss	25 psi (172 kPa)
Backwash Expansion (%)	25 to 50
Operating pH Range	0 to 14
Flow Rate	
Working Service	1-10 gpm/cu.ft. (8-80 BV/h)

REGENERATION DETAILS

Salt Cycle (NaCl)	10 to 15%
Regenerant Level	4-15 lbs/cu.ft. (64.1-240.3 g/L)
Regenerant Flow Rate	0.5-1.5 gpm/cu.ft. (4-12 BV/h)
Regenerant Contact Time	> 20 minutes
Displacement Flow Rate	Same as dilution water
Displacement Volume	10-15 gals/cu.ft. (1-2 BV)
Rinse Flow Rate	Same as service flow
Rinse Volume	35-60 gals/cu.ft. (5-8 BV)

Conforms to §21CFR173.25 of the USFDA Food Additives Regulations

RESINTECH INC.
INNOVATIONS IN ION EXCHANGE

CORPORATE HEADQUARTERS 1801 Federal Street Camden, NJ 08105 USA PHONE 856.768.9600 EMAIL info@resintech.com WEB resintech.com

BACKWASH EXPANSION



The graph above shows the expansion characteristics of ResinTech CG10-MG as a function of flow rate at various temperatures.

CAPACITY



Capacity and leakage data are based on the following: 2:1 Ca:Mg ratio, 500 ppm TDS as CaCO3, 0.2% hardness in the salt and 10% brine concentration applied co-currently through the resin over 30 minutes. No engineering downgrade has been applied.

CERTIFICATIONS

Meets NSF/ANSI/CAN 61

Meets NSF/ANSI/CAN 372

REACH Registered

PACKAGING

Standard

1 cu.ft. Bag | 42 cu.ft. Supersack
1000L Supersack | 25L Bag

Metric

5 cu.ft. Drum | 7 cu.ft. Drum
140L Drum | 200L Drum

Shipping Weight

52 - 54 lbs/cu.ft. (833 - 865 g/L)

MATERIAL SAFETY DATA SHEETS (MSDS)

Material Safety Data Sheets (MSDS) are available for all products on the ResinTech website. They contain important health and safety information that may be needed to protect your employees and customers from any known health and safety hazards associated with our products. We recommend that you secure and study the pertinent MSDS for our products and any other products being used.

These suggestions and data are based on information we believe to be reliable. They are offered in good faith. However we do not make any guarantee or warranty. We caution against using these products in an unsafe manner or in violation of any patents; further we assume no liability for the consequences of any such actions.

Safety Data Sheets (SDS) are available at resintech.com

RESINTECH® INC.
INNOVATIONS IN ION EXCHANGE

CORPORATE HEADQUARTERS 1801 Federal Street Camden, NJ 08105 USA PHONE 856.768.9600 EMAIL info@resintech.com WEB resintech.com