ASM-125

Grade: Standard

Antimony & silica selective, hybrid anion resin, styrene/DVB gel, chloride form

ResinTech ASM-125 is a chloride form antimony selective hybrid gel type 1 strong base anion resin. Hydrated iron oxide is monoatomically dispersed throughout the polymer, giving the product hybrid properties and exceptional capacity for radionuclides such as Antimony 125 and for neutral silica, while retaining its strong base capacity for anionic contaminants. ASM-125 is intended for the removal of Antimony 125 and other radionuclides from radwaste.

FEATURES & BENEFITS

- High Affinity For Antimony And Silica
- Effective In Layered Resin Systems Or In Mixed Beds
- Superior Physical Stability And Controlled Particle Size
- Low Chloride Content
- Patented Material

APPLICATIONS

- Antimony Removal
- Phosphate Removal
- Silica Removal
- Borated Water

PHYSICAL PROPERTIES

Polymer Matrix	Styrene/DVB
Polymer Type	Gel
Ionic Form (as shipped)	Chloride (Cl^-)
Functional Group	Hybrid
Physical Form	Test
Uniformity Coefficient	1.60
Particle Size	16-50 US mesh (297-1190µm)
< 50 mesh (300 µm) %	< 1%
Minimum Sphericity (%)	93
Capacity (meq/mL)	1.40
Moisture Retention (%)	35% to 45%
Shipping Weight	48 - 50 lbs/cu.ft. (769 - 801 g/L)
Color	Black

SUGGESTED OPERATING CONDITIONS

Maximum Temperature	250°F (121°C)
Minimum Bed Depth	12 in. (30.5 cm)
Maximum Pressure Loss	25 psi (172 kPa)
Operating pH Range	4.0 to 10.0
Flow Rate	
Working Service	1-10 gpm/cu.ft. (8-80 BV/h)

RESINTECH® INC.
INNOVATIONS IN ION EXCHANGE

CORPORATE HEADQUARTERS 1801 Federal Street Camden, NJ 08105 USA PHONE 856.768.9600 EMAIL info@resintech.com WEB resintech.com

PRESSURE LOSS

The graph above shows the expected pressure loss of ResinTech ASM-125 per foot of bed depth as a function of flow rate at various temperatures.

BACKWASH EXPANSION

The graph above shows the expansion characteristics of ResinTech ASM-125 as a function of flow rate at various temperatures.

ANTIMONY REMOVAL

Trace levels of antimony are adsorbed by the iron hybrid material inside ResinTech **ASM-125**, which in all other respects remains a strong base anion resin. The resin is typically used as the bottom layer of a multilayer exchange tank. Antimony reduction is typically around 90%. In recycle applications where the source of antimony has been removed, remaining antimony can be reduced below the limit of detection.

REMOVAL OF OTHER TRACE CONTAMINANTS

ResinTech **ASM-125** is also able to remove other traces of activated metal oxides such as nickel, tin, and tellurium.

CERTIFICATIONS

Meets NSF/ANSI/CAN 61

Meets NSF/ANSI/CAN 372

PACKAGING

Standard

1 cu.ft. Bag | 7 cu.ft. Drum
25L Bag | 200 L Drum

Metric

5 cu.ft. Drum | 42 cu.ft. Supersack
140L Drum | 1000 L Supersack

Shipping Weight

48 - 50 lbs/cu.ft. (769 - 801 g/L)

RESINTECH® INC.
INNOVATIONS IN ION EXCHANGE

CORPORATE HEADQUARTERS 1801 Federal Street Camden, NJ 08105 USA PHONE 856.768.9600 EMAIL info@resintech.com WEB resintech.com

MATERIAL SAFETY DATA SHEETS (MSDS)

Material Safety Data Sheets (MSDS) are available for all products on the ResinTech website. They contain important health and safety information that may be needed to protect your employees and customers from any known health and safety hazards associated with our products. We recommend that you secure and study the pertinent MSDS for our products and any other products being used.

These suggestions and data are based on information we believe to be reliable. They are offered in good faith. However we do not make any guarantee or warranty. We caution against using these products in an unsafe manner or in violation of any patents; further we assume no liability for the consequences of any such actions.

Safety Data Sheets (SDS) are available at resintech.com

RESINTECH® INC.
INNOVATIONS IN ION EXCHANGE

CORPORATE HEADQUARTERS 1801 Federal Street Camden, NJ 08105 USA PHONE 856.768.9600 EMAIL info@resintech.com WEB resintech.com