SBG1P-OH-UPS

Grade: Standard

Strong base type 1 anion resin, styrene/DVB gel, uniform particle size, hydroxide form

ResinTech SBG1P-OH-UPS is a uniform particle size, type 1 gel strong base anion resin in the hydroxide form. SBG1P-OH-UPS is intended for use in industrial demineralizing applications such as two beds and mixed beds where economical high purity water production and low TOC is required.

FEATURES & BENEFITS

- Uniform particle size
- Organic fouling resistance
- Superior physical stability
- Complies with US FDA regulations

APPLICATIONS

- High Purity DI Water
- Condensate Polishing
- Ultrapure Water Production (UPW)
- Demineralization / DI
- Mixed Bed Components
- Silica Removal

PHYSICAL PROPERTIES

Polymer Matrix	Styrene/DVB
Polymer Type	Gel
Ionic Form (as shipped)	Hydroxide (OH^-)
Functional Group	Trimethylamine
Physical Form	Spherical Beads
Uniformity Coefficient	1.25
Effective Particle Size	625 +100 µm
< 50 mesh (300 µm) %	< 1
Minimum Sphericity (%)	95
Reversible Swelling	18 to 25% (Cl → OH)
Capacity (meq/mL)	1.00
Moisture Retention (%)	65 to 70
Shipping Weight	41 - 43 lbs/cu.ft. (657 - 689 g/L)
Color	White To Amber

SUGGESTED OPERATING CONDITIONS

Maximum Temperature	140°F (60°C)
Maximum Pressure Loss	20 psi (138 kPa)
Backwash Expansion (%)	25 - 50
Operating pH Range	0 to 14
Flow Rate	
Working Service	1-10 gpm/cu.ft. (8-80 BV/h)

RESINTECH INC.
INNOVATIONS IN ION EXCHANGE

CORPORATE HEADQUARTERS 1801 Federal Street Camden, NJ 08105 USA PHONE 856.768.9600 EMAIL info@resintech.com WEB resintech.com

REGENERATION DETAILS

Hydroxide Cycle (NaOH)	2 to 6%	Displacement Volume	10-15 gals/cu.ft. (1-2 BV)
Displacement Flow Rate	Same as dilution water	Rinse Volume	Minimum of 30 gals/cu.ft. (4 BV)

PRESSURE LOSS



The graph above shows the expected pressure loss of ResinTech SBG1P-OH-UPS per foot of bed depth as a function of flow rate at various temperatures.

BACKWASH EXPANSION



The graph above shows the expansion characteristics of ResinTech SBG1P-OH-UPS as a function of flow rate at various temperatures.

DEMINERALIZATION

ResinTech SBG1P-OH-UPS can be used as the anion component in a variety of demineralization applications where a hydroxide form anion resin is coupled with a hydrogen form cation resin. Common configurations include separate beds, mixed beds and other more complicated arrangements. Regeneration is accomplished with dilute sodium hydroxide, heated when low silica leakage is desired.

CERTIFICATIONS

REACH Registered

PACKAGING

Standard

42 cu.ft. Supersack | 7 cu.ft. Drum
200L Drum | 1000L Supersack

Metric

1 cu.ft. Bag | 5 cu.ft. Drum
25L Bag | 140L Drum

Shipping Weight

41 - 43 lbs/cu.ft. (657 - 689 g/L)

RESINTECH® INC.
INNOVATIONS IN ION EXCHANGE

CORPORATE HEADQUARTERS 1801 Federal Street Camden, NJ 08105 USA PHONE 856.768.9600 EMAIL info@resintech.com WEB resintech.com

MATERIAL SAFETY DATA SHEETS (MSDS)

Material Safety Data Sheets (MSDS) are available for all products on the ResinTech website. They contain important health and safety information that may be needed to protect your employees and customers from any known health and safety hazards associated with our products. We recommend that you secure and study the pertinent MSDS for our products and any other products being used.

These suggestions and data are based on information we believe to be reliable. They are offered in good faith. However we do not make any guarantee or warranty. We caution against using these products in an unsafe manner or in violation of any patents; further we assume no liability for the consequences of any such actions.

Safety Data Sheets (SDS) are available at resintech.com

RESINTECH® INC.
INNOVATIONS IN ION EXCHANGE

CORPORATE HEADQUARTERS 1801 Federal Street Camden, NJ 08105 USA PHONE 856.768.9600 EMAIL info@resintech.com WEB resintech.com