CG8-H-BL-NX

Grade: Standard

Strong Acid Black Cation Resin, Polystyrenic Gel crosslinked with 8% Divinylbenzene, Hydrogen Form (NxStage Spec)

ResinTech CG8-H-BL-NX is a dark-colored hydrogen form 8% crosslinked gel strong acid cation resin specifically engineered for use with NxStage filters. It is a workhorse cation resin with properties similar to other products in the CG8 family. CG8-H-BL-NX is intended for use in all industrial applications such as demineralization where a hydrogen form cation resin is required and for mixed beds where its dark color makes visual identification of the cation/anion interface plainly evident.

FEATURES & BENEFITS

- Hydrogen form
- Medical softening and demineralizing applications
- Low color throw
- Superior physical stability
- Complies with US FDA regulations

APPLICATIONS

- Ammonia Removal
- Iron Removal
- Softening

PHYSICAL PROPERTIES

Polymer Matrix	Styrene/DVB
Polymer Type	Gel
Ionic Form (as shipped)	Hydrogen (H^+)
Functional Group	Sulfonic Acid
Physical Form	Spherical Beads
Uniformity Coefficient	1.60
Particle Size	16-50 US mesh (297-1190µm)
< 50 mesh (300 µm) %	< 1%
Minimum Sphericity (%)	93
Reversible Swelling	5 to 9% (Na → H)
Capacity (meq/mL)	1.80
Moisture Retention (%)	47 to 56
Shipping Weight	49 - 51 lbs/cu.ft. (785 - 817 g/L)
Color	Dark Brown to Black

SUGGESTED OPERATING CONDITIONS

Maximum Temperature	265°F (129°C)
Minimum Bed Depth	24 in. (61.0 cm)
Maximum Pressure Loss	25 psi (172 kPa)
Backwash Expansion (%)	25 to 50
Operating pH Range	0 to 14
Flow Rate	
Working Service	1-10 gpm/cu.ft. (8-80 BV/h)

REACH COMPLIANCE

RESINTECH® INC.
INNOVATIONS IN ION EXCHANGE

CORPORATE HEADQUARTERS 1801 Federal Street Camden, NJ 08105 USA PHONE 856.768.9600 EMAIL info@resintech.com WEB resintech.com

BACKWASH EXPANSION



The graph above shows the expansion characteristics of ResinTech CG8-H-BL-NX as a function of flow rate at various temperatures.

CAPACITY



Capacity and leakage data are based on the following: 2:1 Ca:Mg ratio, 500 ppm TDS as CaCO3, 0.2% hardness in the salt and 10% brine concentration applied co-currently through the resin over 30 minutes. No engineering downgrade has been applied.

CERTIFICATIONS

REACH Registered

Shipping Weight

49 - 51 lbs/cu.ft. (785 - 817 g/L)

MATERIAL SAFETY DATA SHEETS (MSDS)

Material Safety Data Sheets (MSDS) are available for all products on the ResinTech website. They contain important health and safety information that may be needed to protect your employees and customers from any known health and safety hazards associated with our products. We recommend that you secure and study the pertinent MSDS for our products and any other products being used.

These suggestions and data are based on information we believe to be reliable. They are offered in good faith. However we do not make any guarantee or warranty. We caution against using these products in an unsafe manner or in violation of any patents; further we assume no liability for the consequences of any such actions.

Safety Data Sheets (SDS) are available at resintech.com

RESINTECH® INC.
INNOVATIONS IN ION EXCHANGE

CORPORATE HEADQUARTERS 1801 Federal Street Camden, NJ 08105 USA PHONE 856.768.9600 EMAIL info@resintech.com WEB resintech.com