INRICHTING ERKEND BIJ TOEPASSING VAN DE BESLUITWET VAN 30 JANUARI 1947 / ETABLISSEMENT RECONNU PAR APPLICATION DE L'ARRÊTE-LOI DU 30 JANVIER 1947

Centexbel
Technologiepark 70
9052 ZWIJNAARDE

Your notice of	Your reference	Date
08-03-2022		30-03-2022

Analysis Report 22.01331.01

Required tests :
ISO 9073-6 (2000) **Determination of liquid absorbency capacity**

Sample id	Information given by the client	Date of receipt
T2204649		08-03-2022

Joceleyne Coreelman
Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.

INRICHTING ERKEND BIJ TOEPASSING VAN DE BESLUITWET VAN 30 JANUARI 1947 / ETABLISSEMENT RECONNU PAR APPLICATION DE L'ARRÊTE-LOI DU 30 JANVIER 1947

Determination of liquid absorbency capacity

Date of ending the test	29-03-2022
Standard used	ISO 9073-6 (2000)
Deviation from the standard	-
Conditioning	20°C, relative humidity 65%
Number of test specimens	5
Dimension of the specimens	100 mm x 100 mm
Used liquid	Water demineralize
Influence time	60 s
Drainage time	120 s

60 sec	T2204649				
Proefstuk	Massa voor	Massa na	Wateropname %	g wateropname/100cm² (= ml/100cm²)	l/m²
1	29.080	53.084	82.5	24.004	2.400
2	28.356	51.488	81.6	23.132	2.313
3	29.311	53.867	83.8	24.556	2.456
4	29.838	54.858	83.9	25.020	2.502
5	29.513	54.238	83.8	24.725	2.473
	29.2	53.5	83.1	24.3	2.4